

Quality Standards of OK primer

21.06.2017

Test section		Unit	Specification	Sampling	Test cycle		etc.
					Hanwha L&C	Cooperative firm	
Appearance	Color	-	ivory white				
Test of measurement	Solid powder	%	58 ± 2	1 Sample/Lot	once/Lot	once/Lot	
	Viscosity	CPS	7,000 ± 2,000				
Inspection Reliability	Bonding strength	kgf/25mm	2.6				
	Edge peeling	-	not peel off				
	Adhesion test between film and MDF	fast peeling low peeling	%	over 60% of MDF sawdust over 10% of MDF sawdust			